



Product description:

It is a two-component glossy urea white based on short non-air-drying oil resins and amine resins, and on wooden surfaces that are exposed to the conditions , it is used both internally and externally.

Application:

This coating as the final layer on the wood surface for protection and beauty is applied the outstanding features of the coating include excellent adhesion to the surface, hardness, good flexibility, good gloss, resistance to abrasion, oil secretions, vegetable and animal oils.

Technical data:

WOOD ALKYD PAINT – GLOSSY UREA FOR WOOD (AMV • 9016)

Specification	Details	EN Standard	ASTM Standard
Sheen (Gloss Level)	White and colored	EN ISO 2813	D523
Solids by Volume %	30 ± 2	EN ISO 3233-1 / 3233-2	D2697
Solids by Weight %	55 ± 2	EN ISO 3251	D2369
Density / Specific gravity g/cm ³	0.95 + 1.1 gr/cm ³	EN ISO 2811	D1475
Dry Film Thickness (DFT) μm	25 - 35 μ	EN ISO 2808	D7091
Wet Film Thickness (WFT) μm	85 - 95 μ	EN ISO 2808	D4414
Gloss @ 20°	80	EN ISO 2813	D523
Surface Drying Time	Max 60 min	EN ISO 9117-3	D1640
Deep Drying (Through Dry)	Max 8 hours	EN ISO 9117-1	D1640
Hardening mechanism	Solvent evaporation	EN ISO	D

The drying time depends on the thickness of the applied film, the ambient temperature, the humidity of the environment and the wind flow. All information in this catalog is based on dry film thickness in laboratory conditions.

Environmental Conditions:

This product can be run at 5-35°C on dry place.

Equipment Used:

Airless spray:

Nozzle diameter: 0.15 - 0.21 inches,

Output pressure: minimum 141 air spray times

Air spray:

Nozzle diameter: 1.8 - 2 mm,

Nozzle pressure: 2 - 4 times

Surface Preparation: In order to prepare wooden surfaces, you can first use sealer and after sanding the sealed wood, use killer and nitrocellulose putty and then apply shiny alkyd polish.

Method of Applying: All equipment should be cleaned with the recommended thinner before use. Apply the polish with an appropriate amount of thinned oil thinner and then apply it using a roller, brush or spray.

Safety Tips: This cover is flammable and should be kept away from flame and heat. Also, the operator is obliged to study and comply with the MSDS conditions of this product, use a special mask and safety gloves while using it, and perform the operation in an environment with proper ventilation.


packing:

Quart (Metal can)

Gallon (Metal can)

Storage Conditions: It should be stored in an open space and away from direct sunlight at a temperature of 5-35 °C. Our guarantee is the storage time of the product for 1 years.

Considerations: The available information is based on our technical knowledge and laboratory research, but since the conditions and methods of application are different and out of reach, we do not guarantee the results of it



LEGAL NOTES : The information contained in this Technical Data Sheet is based on laboratory testing and practical experience. Actual performance may vary depending on substrate condition, application method, and environmental conditions. Users should test suitability before large-scale application.

Head Office : Building No.15 , Qasimlu Street 40, Shahidan Zargata Quarter 24, Zone 1, Sulaymaniyah 46001, Iraq

Factory : Tanjaro Industrial Area – Sulaymaniyah – Iraq