

**ACRYLIC PAINT – ACRYLIC PRIMER (SULOSTAR 100 / 106)****Product description:**

This product is based on acrylic emulsion polymer in the form of a pigment-free coating, which, in addition to protecting surfaces against water penetration and atmospheric conditions, fills voids and creates better adhesion of the next layer to the surface. In addition, this product can also be used to make putty.

Application:

This product is used by creating a sticky layer with excellent penetration ability to be used on plaster, cement, concrete surfaces, interior and exterior of the building.

Technical data:

Specification	Details	EN Standard	ASTM Standard
Appearance	Liquid Viscose	EN ISO 7724	D2244
Shades(color)	Colorless	EN ISO 7724	D2244
Density g/cm3	0.9 - 1 gr/cm3	EN ISO 2811	D1475
Viscosity	65-90 Krebs for primer 100 and 55-65 Krebs for primer 106	EN ISO 2431	D1200
Theoretical coverage	Minimum 10 m2/lit	EN ISO 6504-1	D344
Surface Drying	Maximum 30 minutes	EN ISO 9117	D1640
Through Dry(Deep Drying)	Up to 2 hours	EN ISO 9117-1	D1640

Environmental Conditions:

This product can be run at 5 - 35°C on dry place.

**Surface Preparation:**

The surface must be clean, dry and free from any contamination.

Method of Applying:

Mix the primer with water in a ratio of 1 to 1 and apply one layer on all the desired surfaces. Apply the top color after at least an hour. Do not re-apply on the parts that have already been primed and dried.

Equipment Used: Spray, brush, roller

Safety Tips:

This product is water-based and non-flammable. But it is recommended that in case of skin contact, wash it with soap and large amounts of water and consult a doctor in case of skin sensitivity and irritation.

Storage Conditions:

This product should be in a closed space and away from direct rays .The temperature should be kept at 5 - 35 degrees Celsius.

packing:**Silo100**

Quart (Metal can)

Galon (Metal can)

5 Gall (Metal can)

Silo106

Galon (Plastic can)

Considerations:

The available information is based on our technical knowledge and laboratory research, but since the conditions and methods of application are different and out of reach, we do not guarantee the results of it.

LEGAL NOTES : : The information contained in this Technical Data Sheet is based on laboratory testing and practical experience. Actual performance may vary depending on substrate condition, application method, and environmental conditions. Users should test suitability before large-scale application.

Head Office : Building No.15 , Qasimlu Street 40, Shahidan Zargata Quarter 24, Zone 1, Sulaymaniyah 46001, Iraq

Factory : Tanjaro Industrial Area – Sulaymaniyah – Iraq